



## SAFFIL

*Start saving energy now.  
Contact your local distributor.*

**Unifrax Ltd.**

T:+44 (0)1744 88 7600

F:+44 (0)1744 88 9916

[www.unifrax.com](http://www.unifrax.com)

### DESCRIPTION

Saffil Felt is manufactured from high purity polycrystalline wool, blended with specially selected organic binders to give flexible felts with exceptional characteristics. Designed for use up to 1600°C, the resultant sheets are intumescent, self supporting and lightweight with exceptional thermal performance characteristics. Upon initial firing the organic binder burns out completely at temperatures in excess of 400°C and an expansion in the product's thickness occurs.

### GENERAL CHARACTERISTICS

Saffil Felt has the following outstanding characteristics:

- High temperature stability (up to 1600°C)
- Low thermal conductivity
- Virtually 'shot' free
- Resistance to thermal shock & chemical attack
- Excellent flexibility & high temperature resiliency
- Insoluble in water
- Expansion up to 3 times original thickness

### TYPICAL APPLICATIONS

- Expansion joints in industrial furnace linings
- Strips in new fibre module linings to overcome shrinkage
- Gap filling for lining maintenance / repair
- High temperature gaskets and seals

The UNIFRAX logo is located in the bottom right corner. It features the word "UNIFRAX" in a bold, white, sans-serif font, set against a dark blue background. The letters are slightly shadowed, giving the logo a three-dimensional appearance.

## TYPICAL PRODUCT PARAMETERS

Saffil Felt	
<b>Typical Chemical Analysis (fibre wt. %)</b>	
Al <sub>2</sub> O <sub>3</sub>	95 - 97
SiO <sub>2</sub>	3 - 5
Trace	<0.5
<b>Physical Properties</b>	
Colour	White
Classification Temperature (°C) *	1600
Product Density (kg/m <sup>3</sup> )	160
Product Thickness (mm) *	8
Loss on Ignition (wt. %)	
from Fibre	0
from Felt	<12

\*Classification Temperature is not a definition of the operational limit of these products, especially when long term physical or dimensional stability is a factor. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office.

\* Thickness variation can be +/- 2mm on nominal.

## AVAILABILITY

Thickness (mm)	Sheet Size (mm)	Sheets per Carton
8	700 x 550	20

## HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

**Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation.** Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.