

Saffil Mat

Description

Saffil Mat is a high temperature, un-needed, polycrystalline wool product. It is produced by a unique solution extrusion process which ensures the highest level of chemical purity and lowest level of 'shot' (non-fibre particles). The Mat is completely inorganic and retains its flexibility and thermal properties in many working environments, up to 1600°C. Saffil Mat can be used in a wide variety of applications and is especially suited to environments where the presence of 'shot' is undesirable or where resistance to corrosive agents is essential.

General Characteristics

Saffil Mat has the following outstanding characteristics:

- High temperature stability (up to 1600°C)
- Low thermal conductivity
- Virtually 'shot' free
- Resistance to thermal shock & chemical attack
- Excellent flexibility & resiliency
- Insoluble in water



Typical Applications

- High temperature furnace, boiler & kiln linings
 - Blast, forging, re-heat & heat treatment
 - Ethylene, catalyst & sulphur heaters and reformers
 - Porcelain, refractory, laboratory & dental kilns
- Speciality applications
 - Filtration
 - Acoustic insulation
 - Filler for insulating textile structures
 - Semiconductor processing & fuel cell components

Typical Product Parameters

Saffil Matt		
<i>Typical Chemical Analysis (fibre wt. %)</i>		
Al ₂ O ₃		95 – 97
SiO ₂		3 – 5
Trace		<0.5
<i>Physical Properties</i>		
Colour		White
Classification Temperature (°C)*		1600
Median Fibre Diameter (microns)		3 – 4
Product Density (kg/m ³)		35
Specific Heat at 1000°C (J/kgK)		1000
<i>Thermal Conductivity (W/mK)</i>		
Mean Temp.		
800°C		0.29
1000°C		0.39
1200°C		0.51
<i>Permanent Linear Shrinkage (%) 6 Hour Soak</i>		
1500°C		<4

*Classification Temperature is not a definition of the operational limit of these products, especially when long term physical or dimensional stability is a factor. For certain applications, continuous use temperature limits may be significantly reduced. For assistance or clarification, please contact your nearest Unifrax Engineering office.

Availability

Thickness (mm)	Roll Width (mm)	Roll Length (m)
35	610	14.8

All product dimensions provided are nominal dimensions.

Handling Information

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

The following is a registered trademark of Unifrax I LLC: Saffil.

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.

Form U-413 EN
Effective 9/18
© 2018 Unifrax I LLC
All Rights Reserved
Page 2 of 2

Saffil®

Unifrax I LLC
European Sales & Marketing
Headquarters
Unifrax Limited
Mill Lane, Rainford,
St. Helens, Merseyside
England, WA11 8LP
Telephone: +44 (0)1744 88 7600
Internet: www.unifrax.com
Email: info@unifrax.com