



## DESCRIPTION

Unifrax 1600 Saffil Paper products are manufactured from high purity polycrystalline wool, blended with specially selected organic binders to give a flexible paper with exceptional characteristics. This high temperature paper can be exposed to temperatures up to 1600°C, has excellent chemical resistance and is virtually free of 'shot' (unfiberised particles). Advanced production techniques ensure a highly uniform structure enhanced by low thermal conductivity, good handling strength and a smooth surface. 1600 Papers are available in a range of thicknesses and roll sizes.

## GENERAL CHARACTERISTICS

1600 Paper has the following outstanding characteristics:

- High temperature stability (up to 1600°C)
- Resistance to chemical attack
- Good handling strength
- Excellent flexibility
- Easy to wrap, cut and shape

## TYPICAL APPLICATIONS

- High temperature expansion joints and seals
- Laboratory furnace linings
- Separation media for metal/ceramic processes
- Battery and electrical equipment insulation

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

*Start saving energy now.  
Contact your local distributor.*

**Unifrax Ltd.**

T:+44 (0)1744 88 7600

F:+44 (0)1744 88 9916

[www.unifrax.com](http://www.unifrax.com)

## TYPICAL PRODUCT PARAMETERS

1600 Saffil Paper	
<b>Typical Chemical Analysis (fibre wt. %)</b>	
Al <sub>2</sub> O <sub>3</sub>	>90.0
SiO <sub>2</sub>	<8.0
Trace	<2.0
<b>Physical Properties</b>	
Colour	White
Product Density (kg/m <sup>3</sup> )	140 - 200
Classification Temperature (°C) *	1600
Loss on Ignition (wt. %)	~7
<b>Thermal Conductivity (W/mK)</b>	
<b>Mean Temp.</b>	
600 °C	0.16
800 °C	0.20
1000 °C	0.24
<b>Permanent Linear Shrinkage (%) 24 Hour Soak</b>	
1600 °C	<4.0

\*Classification Temperature is not a definition of the operational limit of these products, especially when long term physical or dimensional stability is a factor. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties data measured according to EN 1094-1.

The test data shown are average results of tests conducted under standard procedures and are subject to variation. Results should not be used for specification purposes.

## AVAILABILITY

Thickness (mm)	Roll Width (mm)	Roll Length (m)
1	550	19
2	550	19
3	550	19

Other thicknesses / sizes may be available on request subject to minimum order requirements.

## HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

**Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation.** Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.